

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 128.7 mm
- Effective Area (A_e): 237.0mm²
- Effective Area (A_{Min}): 237.0mm²
- Effective Volume (V_e): 30516mm³

Approximate weight : 155g/pc




T5030 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	Ordering code
CF196	2000 ±20%	4600+30%/-20%	CF196T5030
CF139	2100 ±20%	4850+30%/-20%	CF139T5030
CF130	3000 ±20%	6950+30%/-20%	CF130T5030
CF195A	5000 ±20%	11500+30%/-20%	CF195AT5030
CF265	5000 ±20%	11500+30%/-20%	CF265T5030
CF190	6000 ±20%	13800+30%/-20%	CF190T5030
CF197	7000 ±20%	16200+30%/-20%	CF197T5030
CF199	9000 ±20%	18500 ±30%	CF199T5030

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	50.0	51.0	49.0
B	34.0	34.8	33.2
C	30.0	30.6	29.4



For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf