

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 97.1 mm
- Effective Area (A_e): 77.5mm²
- Effective Area (A_{Min}): 77.5mm²
- Effective Volume (V_e): 7525mm³

Approximate weight : 38.9g/pc




T3813 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	Ordering code
CF196	2000 $\pm$ 20%	2000+30%/-20%	CF196T3813
CF139	2100 $\pm$ 20%	2100+30%/-20%	CF139T3813
CF130	3000 $\pm$ 20%	3000+30%/-20%	CF130T3813
CF195A	5000 $\pm$ 20%	5000+30%/-20%	CF195AT3813
CF265	5000 $\pm$ 20%	5000+30%/-20%	CF265T3813
CF190	6000 $\pm$ 20%	6000+30%/-20%	CF190T3813
CF197	7000 $\pm$ 20%	7000+30%/-20%	CF197T3813
CF199	9000 $\pm$ 20%	8500 $\pm$ 30%	CF199T3813

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	38.1	38.6	37.6
B	25.4	25.9	24.9
C	12.7	12.9	12.5



For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf

Regd. Office & Works: Jabli, Distt. Solan, Himachal Pradesh – 173 209 (India)

Tel: +91 1792 277231/32/36, Fax: +91 1792 277234

E-mail: sales@cosmoferrites.com