

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards.

Effective Parameters irrespective of material grade (per piece)

- Effective Length (L_e): 16.4 mm
- Effective Area (A_e): 8.25mm²
- Effective Area (A_{Min}): 8.25mm²
- Effective Volume (V_e): 135.0mm³

Approximate weight : 0.6g/pc




T0704A OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability (μ_{iac})	AL Value (nH)	Ordering code
CF196	2000 $\pm$ 20%	1250+30%/-20%	CF196T0704A
CF139	2100 $\pm$ 20%	1350+30%/-20%	CF139T0704A
CF130	3000 $\pm$ 20%	1900+30%/-20%	CF130T0704A
CF195A	5000 $\pm$ 20%	3150+30%/-20%	CF195AT0704A
CF265	5000 $\pm$ 20%	3150+30%/-20%	CF265T0704A
CF190	6000 $\pm$ 20%	3800+30%/-20%	CF190T0704A
CF197	7000 $\pm$ 20%	4400+30%/-20%	CF197T0704A
CF199	9000 $\pm$ 20%	5700 $\pm$ 30%	CF199T0704A

Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	7.6	7.8	7.4
B	3.4	3.5	3.3
C	4.1	4.3	3.9



For general terms and conditions please visit: http://www.cosmoferrites.com/Downloads/Downloads/bcb70e7c-ae33-40ec-a881-0d5120db57b6_GTC.pdf

Regd. Office & Works: Jabli, Distt. Solan, Himachal Pradesh – 173 209 (India)

Tel: +91 1792 277231/32/36, Fax: +91 1792 277234

E-mail: sales@cosmoferrites.com